



NCP Coatings Inc.

Asphalt Coatings

Black Pipe Coating NSF Approved

Technical Data Sheet

Intended Uses: Black Asphalt Coating Used On Ductile Iron And Steel Pipe To Prevent Rusting.

PRODUCT INFORMATION

Color:	Black	Theoretical Coverage:	760sq. ft/gal.
Gloss:	90% on 60 Degree	Salt Spray Test:	N/A
Volume Solids:	48.96%	Humidity Test:	N/A
Weight Solids:	56.99%	Weatherometer Test:	N/A
Weight per Gallon:	7.25-7.3lb/gal.	Pencil Hardness:	2B @ 72 Hrs
VOC:	3.5 lb/gal.	Viscosity:	80-135 sec #4 Ford
Film Thickness:	2.0 Mil DFT		

APPLICATION INFORMATION

Methods:	AAA, Airless
Mix Ratio:	N/A
Reducer:	VOC compliant, Reduce only if lawful
Cleaner:	Xylene, or similar solvent
Pot Life:	N/A
Dry Time:	Air dry, Force cure
Time To Recoat:	N/A

SURFACE PREPARATION

Surface should be clean of all grease, dirt, oil, rust and foreign material which would be detrimental to the coating.

SAFETY INFORMATION

Consult the Material Safety Data Sheet prior to application for detailed information on the health and safety hazards.

CAUTION: This Product is for Industrial use Only!

STORAGE

This product must be stored in accordance with local, state, and national regulations. Preferred storage conditions: Keep containers in a dry space with adequate ventilation. The containers should remain tightly sealed when not in use. Handle with care. Stir well before use.

DRY TIME / CURE

Cure is a function of time, temperature, and film build. Should be dust free in less than 1 hour. Through cure a function of DFT.

COMMENTS

USE OF A MECHANICAL MIXER IS HIGHLY RECOMMENDED. Niles part number N-2819A is a slow dry softer asphalt containing more Mineral Spirits than Naphtha. N-3613 is a fast dry asphalt.

NOTE: The above information is supplied as a guideline to our customers. The user must be aware of the cleaning, pretreatment, application and testing requirements for their specific job!

225 Fort Street, Niles, MI. 49120
Phone: (800) 627-1948 (616) 683-3377
Fax: (616) 683-3305