

Intended Uses: This enamel resists spontaneous ignition when heated by conduction through a metal substrate.

PRODUCT INFORMATION

Color:	See Listing	Theoretical Coverage:	950 sq. ft/gal
Gloss:	45-60 @ 60 degrees	Salt Spray Test:	N/A
Volume Solids:	62.8 %	Humidity Test:	N/A
Weight Solids:	80.4%	Weatherometer Test:	N/A
Weight per Gallon:	13.65 Lbs.	Pencil Hardness:	2B @ 72 hrs
VOC:	2.8 Lbs./Gal. [340 gm./L]	Viscosity:	80-90 KU
Film Thickness:	2-3 mils		

APPLICATION INFORMATION

Methods:	Spray (conventional air, airless, AA/A) brush and roller
Mix Ratio:	N/A
Reducer:	N/A
Cleaner:	Mineral Spirits
Pot Life:	Surface skinning
Dry Time:	2-3 hours to touch
Time To Recoat:	24 hours

SURFACE PREPARATION

This enamel is intended for application over previously painted or primed metal surfaces. The surface must be clean, dry and free of loose paint, rust, oil and grease. If surface is rusted remove rust, feather painted surface and apply primer. Wait for primer to dry(in accordance with manufactures recommendation, then apply fire-retardant coating.

SAFETY INFORMATION

Consult the Material Safety Data Sheet prior to application for detailed information on the health and safety hazards.

CAUTION: This Product is for Industrial use Only!

STORAGE

Store in accordance with local, state and federal regulations. Store in a dry area.

DRY TIME / CURE

2 hours to touch

COMMENTS

This enamel is not intended to prevent the burning of wood or other combustible substrates.

NOTE: The above information is supplied as a guideline to our customers. The user must be aware of the cleaning, pretreatment, application and testing requirements for their specific job!