

Intended Uses: General purpose interior and exterior primer for application to either steel or aluminum.

PRODUCT INFORMATION

<i>Color:</i>	Yellow #33793	<i>Theoretical Coverage:</i>	900 sq ft @ 100% Transfer efficiency @ 1 mil DFT
<i>Gloss:</i>	10 max. @ 60°	<i>Salt Spray Test:</i>	500 hours (ASTM B-117)
<i>Volume Solids:</i>	57.8%	<i>Humidity Test:</i>	N/A
<i>Weight Solids:</i>	78.9%	<i>Weatherometer Test:</i>	N/A
<i>Weight per Gallon:</i>	13.65 Lbs.	<i>Pencil Hardness:</i>	4B @ 72 hours
<i>VOC:</i>	2.8 Lbs./Gal. [340g/L]	<i>Viscosity:</i>	75-95 KU
<i>Film Thickness:</i>	2-3 mils DFT		

APPLICATION INFORMATION

<i>Methods:</i>	Spray (conventional air, airless, AA/A) brush and roller
<i>Mix Ratio:</i>	N/A
<i>Reducer:</i>	N/A
<i>Cleaner:</i>	Mineral spirits
<i>Pot Life:</i>	N/A
<i>Dry Time:</i>	4-6 hours to touch
<i>Time To Recoat:</i>	6-8 hours

SURFACE PREPARATION

Remove all wax, dirt, grease, rust and oil. If surface is rusted, remove rust, feather painted surface and apply primer to clean bare steel. If primer is to be applied to a good previously painted surface light sanding of the painted surface should be done.

SAFETY INFORMATION

Consult the Material Safety Data Sheet prior to application for detailed information on the health and safety hazards.

CAUTION: This Product is for Industrial use Only!

STORAGE

Store in accordance with local, state and federal regulations. Store in a dry area.

DRY TIME / CURE

Dry to touch 4-6 hours, dry hard 8 hours @ 1 mill DFT.

COMMENTS

NOTE: The above information is supplied as a guideline to our customers. The user must be aware of the cleaning, pretreatment, application and testing requirements for their specific job!