

Intended Uses: A zinc rich alkyd primer designed fro priming welds on galvanized steel.

### **PRODUCT INFORMATION**

<i>Color:</i>	Grey	<i>Theoretical Coverage:</i>	1050 sq. ft/gal @ 1 mil
<i>Gloss:</i>	N/A	<i>Salt Spray Test:</i>	Pass 288 hrs
<i>Volume Solids:</i>	65.6%	<i>Humidity Test:</i>	N/A
<i>Weight Solids:</i>	91.8%	<i>Weatherometer Test:</i>	N/A
<i>Weight per Gallon:</i>	29.60 lbs/gal	<i>Pencil Hardness:</i>	H @ 48 hours
<i>VOC:</i>	2.50 lbs/gal max (300 g/L)	<i>Viscosity:</i>	80-95 KU
<i>Film Thickness:</i>	1.0-2.0 mils		

### **APPLICATION INFORMATION**

<i>Methods:</i>	Designed for brush application
<i>Mix Ratio:</i>	N/A
<i>Reducer:</i>	Mineral Spirits or Aromatic Naphtha
<i>Cleaner:</i>	Mineral Spirits or Aromatic Naphtha
<i>Pot Life:</i>	N/A
<i>Dry Time:</i>	30 minutes dry to touch; 8 hours hard dry
<i>Time To Recoat:</i>	24 hours

### **SURFACE PREPARATION**

Surface should be clean of all grease, dirt, oil, rust and foreign material which would be detrimental to the coating.

### **SAFETY INFORMATION**

Consult the Material Safety Data Sheet prior to application for detailed information on the health and safety hazards.

**CAUTION:** This Product is for Industrial use Only!

### **STORAGE**

This product must be stored in accordance with local, state, and national regulations. Preferred storage conditions: Keep containers in a dry space with adequate ventilation. The containers should be tightly sealed. Handle with care. Stir well before use.

### **DRY TIME / CURE**

### **COMMENTS**

USE OF A MECHANICAL MIXER IS HIGHLY RECOMMENDED. Niles part number is N-7222.

***NOTE:*** The above information is supplied as a guideline to our customers. The user must be aware of the cleaning, pretreatment, application and testing requirements for their specific job!