

*Intended Uses:* A high-grade acrylic water based emulsion enamel designed for primed metal, particularly on smooth exterior metal.

### **PRODUCT INFORMATION**

<i>Color:</i>	Various Colors available	<i>Theoretical Coverage:</i>	550 sq. ft @1 mil
<i>Gloss:</i>	1-85 % @ 60°	<i>Salt Spray Test:</i>	N/A
<i>Volume Solids:</i>	33-36%	<i>Humidity Test:</i>	N/A
<i>Weight Solids:</i>	42-52%	<i>Weatherometer Test:</i>	300 hours
<i>Weight per Gallon:</i>	10.6 – 11.5 lbs/gal	<i>Pencil Hardness:</i>	2B@ 72 hours
<i>VOC:</i>	2.0 lbs/gal max	<i>Viscosity:</i>	99 KU maximum
<i>Film Thickness:</i>	3.0 mils DFT		

### **APPLICATION INFORMATION**

<i>Methods:</i>	Spray (conventional, air, airless, AA/A), brush and roller.
<i>Mix Ratio:</i>	N/A
<i>Reducer:</i>	Water
<i>Cleaner:</i>	Water
<i>Pot Life:</i>	N/A
<i>Dry Time:</i>	Air dry 2 hrs max
<i>Time To Recoat:</i>	6 hours

### **SURFACE PREPARATION**

Surface should be clean of all grease, dirt, oil, rust and foreign material which would be detrimental to the coating. For previously painted surfaces in good condition, sand lightly prior to application. For heavily rusted areas,, spot prime and allow to cure for 24 hours.

### **SAFETY INFORMATION**

Consult the Material Safety Data Sheet prior to application for detailed information on the health and safety hazards.

**CAUTION:** This Product is for Industrial use Only!

### **STORAGE**

This product must be stored in accordance with local, state, and national regulations. Preferred storage conditions: Keep containers in a dry space with adequate ventilation. The containers should be tightly sealed. Handle with care. Stir well before use. Shelf life is 1 year from date of manufacture.

### **DRY TIME / CURE**

Air dry to touch 2 hrs max

### **COMMENTS**

USE OF A MECHANICAL MIXER IS HIGHLY RECOMMENDED. This coating is available in LSA and LRC standards. This family of products does withstand DS2 decontamination.

***NOTE:*** The above information is supplied as a guideline to our customers. The user must be aware of the cleaning, pretreatment, application and testing requirements for their specific job!