

**Intended Uses:** Over primed metal to be highly weather resistant. Excellent color and gloss retention.

### **PRODUCT INFORMATION**

<b>Color:</b>	See listing for available colors	<b>Theoretical Coverage:</b>	900 sq. ft. @ 100% transfer efficiency @ 1mil DFT
<b>Gloss:</b>	1% to Full @ 60	<b>Salt Spray Test:</b>	N/A
<b>Volume Solids:</b>	58% - 60%	<b>Humidity Test:</b>	N/A
<b>Weight Solids:</b>	76% - 80%	<b>Weatherometer Test:</b>	300 hours
<b>Weight per Gallon:</b>	11.6 - 12.2 Lbs./Gal.	<b>Pencil Hardness:</b>	2B at 72 hours
<b>VOC:</b>	2.8 Lbs./Gal. Max	<b>Viscosity:</b>	99 KU max
<b>Film Thickness:</b>	3 mils DFT		

### **APPLICATION INFORMATION**

<b>Methods:</b>	Spray (conventional air, airless, AA/A), brush and roller
<b>Mix Ratio:</b>	N/A
<b>Reducer:</b>	Oxsol 100 if required
<b>Cleaner:</b>	Mineral Sprits
<b>Pot Life:</b>	Surface skinning will appear on open containers.
<b>Dry Time:</b>	2-4 hours dry to touch
<b>Time To Recoat:</b>	24 hrs minimum

### **SURFACE PREPARATION**

This is high-grade silicone alkyd copolymer air-dry enamel and is designed for use on primed or pre-painted surfaces. The surface must be clean, dry, and free of loose paint, rust, oil and grease. If the surface is rusted, remove rust prior to painting.

### **SAFETY INFORMATION**

Consult the Material Safety Data Sheet prior to application for detailed information on the health and safety hazards.

**CAUTION:** This Product is for Industrial use Only!

### **STORAGE**

This product must be stored in accordance with local, state, and federal regulations. Keep containers in a dry space with adequate Ventilation. The containers should be tightly sealed. Stir well before using. Shelf life is one (1) year from date of manufacture.

### **DRY TIME / CURE**

2-4 hours dry to touch. Dry through 8 hours at 70 °F @ 1.0 mil DFT.

### **COMMENTS**

This product line is available in 77 colors in low, semi gloss and high-gloss finishes. This product line has been approved by the U.S. Navy and is a QPL(Qualified Products Listing) item.

***NOTE:*** The above information is supplied as a guideline to our customers. The user must be aware of the cleaning, pretreatment, application and testing requirements for their specific job!